

ISA STANDARD - 71.04-2013

Severity Level	G1: MILD	G2: MODERATE	G3: HARSH	G4: SEVERE
Copper reactivity level (in angstroms)*	0 - 299Å	300 - 999Å	1000 - 1999Å	> 2000Å
Silver reactivity level (in angstroms)*	0 - 199Å	200 - 999Å	1000 - 1999Å	> 2000Å

* Normalized to a 30-day exposure

G1 - MILD	Corrosion not a factor in determining equipment reliability.
G2 - MODERATE	Effects of corrosion are measurable and may be a factor in determining equipment reliability.
G3 - HARSH	High probability that corrosive attack will occur.
G4 - SEVERE	Electronic/electrical equipment not expected to survive.



FILTREX

SMART FILTRATION